

3-Chloropropyltriethoxysilane

CAS NO 5089-70-3

**Specification**

Test Item	Test Standard	Test Result	Test Method
Color, APHA	0~15	15	Pt-Co
Assay, %	≥98	98.85	GC
Specific Gravity at 25° C, g/cm <sup>3</sup>	1.000-1.010	1.004	Hydrometer
Refractive Index, N D 20	1.4160-1.4200	1.4200	Abbe Refractometer
Acidity, PH	6.0-7.0	≈6.5	PH paper
Chlorides, ppm	≤100	13.72	Potentiometric Titration
Ethanol, %	≤0.5	0.13	GC

Analyst Wu Yan

Supervisor Yang haijian